

#### First choice for new formulations

# Sudafast™ Red 331

## Pigments for Coatings

# **Product Description**

It is a transparent Naphthol AS pigment. It exhibits high colour strength and good light fastness properties. Recommended for high pigment loading color concentrates for decorative paint applications.

#### **Product Information**

Chemical Type	Naphthol	CAS NO.	6535-46-2
C. I. Name	Pigment Red 112	EINECS / ELINCS NO.	229-440-3
C. I. Constitution No.	12370	Physical Appearance	Red Powder

## **Application Profile**

Decorative Paints	•	Universal Stainers	
Industrial Paints		Water Base Paints	•
Automotive OEM		Powder Coatings	
Automotive Refinish			

• Recommend | O Potential Use | -- Not recommended

### **Technical Performance**

Heat Stability	Overspray Fastness		Full Shade	Tint
140°C	-	Weather Resistance	-	-
		Light Fastness	7	5-6

<b>Physical Properties</b>			
Oil Absorption	44 ± 10%	Bleeding in Xylene	3-4
Specific Gravity	1.40 ± 0.1	Bleeding in Methyl Ethyl Ketone	2-3
Bulk Density (g/ml)	0.18 ± 0.1	Bleeding in Ethyl Acetate	2-3
pH Value	7 - 8	Bleeding in Cellosolve	2-3
Volatile Matter	1% max	Bleeding in Mineral Turpentine	4
Resistance to Acid	5	Specific Surface Area (m <sup>2</sup> /g)	-
Resistance to Alkali	5	Average size of Primary Particle (nm)	-

- ✓ Light fastness: Light fastness rating is assessed on 1 to 8 Blue Wool scale where 1 = 'Poor' and 8 = 'Excellent'.
- ✓ Weather fastness: Weather fastness rating is assessed on 1 to 5 Grey scale where 1 = 'Poor' and 5 = 'Excellent'.
- ✓ Heat stability: Heat stability values given indicate the maximum temperature at which the pigments can be stoved for 10 min. in the full shade and in reductions without undergoing any significant change in shade.
- ✓ Oil absorption: The oil absorption was determined on the basis of EN ISO 787-5 and given in linseed oil per 100 gm. pigment.
- ✓ Solvent bleeding: The bleeding in solvents was tested using the powder grades and the visual rating given on 1 to 5 Grey scale where 1 = 'Heavy bleeding' and 5 = 'No bleeding

The above information is for guidance only and to the best of our knowledge it is accurate and reliable. However, as use conditions are not within our control, no guarantees are given or are to be inferred. Test methods used to generate this data can be provided on request.